



Product Data Sheet

BW-430 Microcrystalline Wax

Description

This light yellow microcrystalline wax has a high melt point that is often needed to increase the congealing point of the wax.

Applications

This wax can be used as water or grease resistant.

BW-430 Microcrystalline Wax Properties		
Test Description	Typical	Range
Congeval Point (D-938)	155° F 68° C	151° - 159° F 66° - 71° C
Needle Penetration (D-1321) 0.1mm @ 77° F/25° C 0.1mm @ 100° F/38° C	25 103	12 - 38 8 - 198
Color	L 1.5	-----

FDA Status: This product is in compliance with Federal Regulations 21 CFR-172.886

Information is subject to change without notification.

Revision Date: 4/1/09

1512 S. Main St. ♦ Oshkosh, WI 54901 ♦ 920-236-8080 ♦ Toll Free 800-294-4692
www.blendedwaxes.com