



Product Data Sheet

BW-2230 Sticktite II

Description

This medium viscosity wax is hard and yellow in color. Used as a foundry utility wax.

Applications

An adhesive wax used for assembling runners and sprue trees.

BW-2217A Non-Filled Foundry Wax Properties		
Test Description	Typical	Range
Congeval Point (D-938)	158° F 70° C	155° - 161° F 68° - 72° C
Needle Penetration (D-1321)		
0.1mm @ 77° F/25° C	4	2 - 6
0.1mm @ 100° F/38° C	50	29 - 71

FDA Status: This product is in compliance with Federal Regulations 21CFR- 172.886 and 21CFR-178.3710.