



Blended Waxes, Inc.

Product Data Sheet

BW-2602A General Purpose Foundry

Description

This is a low viscosity, non-filled utility wax with a hard, smooth surface finish. It is available in a variety of extruded forms.

Applications

This wax is used in extruded forms for investment castings as utility wax for runners and venting.

BW-2602A General Purpose Foundry Wax Properties		
Test Description	Typical	Range
Congeval Point (D-938)	165° F 74° C	162° - 168° F 72° - 76° C
Needle Penetration (D-1321) 0.1mm @ 77° F/25° C 0.1mm @ 100° F/38° C	9 33	3 - 15 18 - 48
Color (Visual)	Yellow	-----

FDA Status: This product is in compliance with Federal Regulations 21CFR- 172.886 and 21CFR-178.3710.

Information is subject to change without notification

Revision Date: 4/1/09

1512 S. Main St ♦ Oshkosh, WI 54902 ♦ (920) 236-8080 ♦ Toll Free 800-294-4692
www.blendedwaxes.com